#### **PCT**

## WORLD INTELLECTUAL PROPERTY ORGANIZATION International Bureau



## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification <sup>5</sup> : C09K 7/02, 7/06	A1	(11) International Publication Number: WO 94/28085 (43) International Publication Date: 8 December 1994 (08.12.94)
(21) International Application Number: PCT/NG (22) International Filing Date: 25 May 1994 (30) Priority Data: 931954 28 May 1993 (28.05.93) 933288 15 September 1993 (15.09. (71) Applicant (for all designated States except US): DEN STATS OLJESELSKAP A.S. [NO/NO]; Forus 300, N-4001 Stavanger (NO). (72) Inventors; and (75) Inventors/Applicants (for US only): SUNDE, Egil Draugveien 30, N-4300 Sandnes (NO). JOHNS Konrad [NO/NO]; Nøtteberget 17, N-7500 Stjørt (74) Agent: TANDBERGS PATENTKONTOR AS; Bok 0306 Oslo (NO).	(25.05.5 93) I NORSI Postbo	(81) Designated States: AT, AU, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, ES, FI, GB, HU, JP, KP, KR, KZ, LK, LU, LV, MG, MN, MW, NL, NO, NZ, PL, PT, RO, RU, SD, SE, SK, UA, US, UZ, VN, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).  Published  With international search report.  In English translation (filed in Norwegian).

## (54) Title: PLUGGING LIQUID FOR PLUGGING A SUBTERRANEAN FORMATION ZONE

#### (57) Abstract

A plugging liquid for plugging of a zone of a subterranean formation around a drill hole, consisting of an emulsion comprising (a) a continuous phase containing a hydrophobic liquid, an emulsifier and a crosslinking agent for a polysaccharide, and (b) a discontinuous phase containing water and a polysaccharide. A variant of the plugging composition contains in addition a weighting material in the discontinuous phase. Also described is a method for preparing the plugging liquid and a method for plugging a zone of a subterranean formation penetrated by a drill hole in fluid communication with the zone, according to which method the new plugging liquid is injected into the zone via the drill hole and is subjected to high shear forces in the drill hole, whereby the polysaccharide and the crosslinking agent are brought into contact with one another with resulting initiation of a crosslinking of the polysaccharide and a setting of the plugging liquid. When the drilling liquid contains a weighting material it is primarily used to inhibit or prevent an undesired blow-out in or from a well.

#### FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

	A	GB	United Kingdom	MR	Mauritania
AT	Austria		<u>*</u>		
ΑÜ	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HŲ	Hungary	NO	Norway
BG	Bulgaria	TE.	Ireland	NZ	New Zealand
BJ	Benin	Π	Italy	PL	Poland
BR	Brazil	JР	Japan	PT	Portugat
BY	Belarus	KE	Kettya	RO	Romania
CA	Canada	KG	Kyrgystan	RÜ	Russian Federation
C#	Central African Republic	KP	Democratic People's Republic	SD	Sudan
CG	Congo		of Korea	SE	Sweden
CH	Switzerland	KR	Republic of Korea	SI	Slovenia
СI	Côte d'Ivoire	KZ	Kazakhstan	SIK	Slovakia
CM	Cameroon	LI	Liectnenstein	SN	Scoegal
CN	China	LK	Sri Lanka	TD	Chad
cs	Czechosłovakia	LU	Luxembourg	TG	Togo
CZ	Czech Republic	LV	Latvia	TJ	Tajikistan
DE	Germany	MC	Monaco	TT	Tripidad and Tobago
DK	Denmark	MD	Republic of Moldova	ÜA	Ukraine
ES	Spain	MG	Madagascar	US	United States of America
FT	Pinland	MIL	Mali	UZ	Uzbekistan
FR	Prance	MIN	Mongolia	VN	Vict Nam
GA	Gabon		-		

# PLUGGING LIQUID FOR PLUGGING A SUBTERRANEAN FORMATION ZONE.

5 This invention relates to a plugging liquid on emulsion basis, a method for its preparation and a method for plugging a zone of a subterranean formation penetrated by a drill hole.

A large number of gel forming compositions are known in the art for use as well control liquids in the drilling of wells for the recovery of oil and gas, for instance in cases where well liquids are lost to the formation or liquid or gas is flowing into the well from the formation. It is known to use polysaccharides for thickening purposes in such known gel forming compositions, see e.g. Norwegian Patents Nos. 116,667 and 161,635, US Patent No. 4,634,538 and British Patent No. 1,406,513.

It is also known to utilize as plugging liquids so-called "rhectropic" liquids. These liquids thicken when subjected to high shear stress. The rheotropic liquid must have physical characteristics enabling it to be easily pumped through the mud system (Condition 1) to the drill bit when leakages occur in the formation. The shear stress created when the liquid is forced through the nozzles of the drill bit, where the pressure drop will be in the range of about 50 to 120 bars, must result in a thickening of the liquid (Condition 2). The time before thickening must however be sufficient for the liquid to flow into and seal the formation.

30

US Pat. No. 4,663,366 (Carr Corporation) discloses a rheotropic liquid of such a nature and an emulsion technique for controlling the thickening of the liquid. According to said patent, a polycarboxylic acid-containing water-in-oil emulsion is used wherein:

- the oil phase contains dispersed therein a hydratable, water-swelling, hydrophilic clay such as bentonite, and additionally contains a solubilized surfactant consisting of a polyamine derivative, and

- the aqueous phase contains dissolved therein a polyacrylamide and a polycarboxylic acid.

It is critical that the bentonite be kept separated from the 5 water until the required thickening of the liquid is initiated. For that purpose each droplet of the dispersed aqueous phase is coated with a membrane or a film of a polymeric material which is formed as a consequence of the aqueous phase being dispersed or emulsified in the oil phase of the emul-The film or membrane is formed as a result of the interfacial interaction between the polyamine derivative in the oil phase and the polyacrylamide and the polycarboxylic acid in the dispersed aqueous phase. When the emulsion is subjected to high shear forces, the protective film around the 15 dispersed droplets in the emulsion is broken and the bentonite comes into contact with the water, thus enabling a swelling of the bentonite and consequently a thickening of the liquid. However, for the rheotropic liquid of US Pat. No. 4,663,366 the obtainable ratio of the thickness of the liquid in 20 Condition 2 to the thickness of the liquid in Condition 1 is lower than is desireable.

There is a need in well control operations for improved plugging liquids which (1) have the lowest possible viscosity in Condition 1, before they are subjected to high shear forces, (2) thickens to a high thickness in Condition 2 aft r having been subjected to high shear forces, (3) maintain their acquired thickness for a longer period of time, and (4) to the least possible extent undergo a thickening in Condition 1 as a result of the emulsion gradually deteriorating during storage or before it has had time to pass through the nozzles of the drill bit in the drill hole.

It is an object of the present invention to provide a plugging liquid exhibiting markedly improved properties compared to the plugging liquids that are available today.

Thus, the invention provides a new plugging liquid for plugging a zone of a subterranean formation around a drill hole,

PCT/NO94/00097 WO 94/28085

consisting of an aqueous liquid containing a polysaccharide. The plugging liquid is characterized in that it consists of an emulsion comprising:

a) 5 - 50% by volume of a continuous phase containing:

800 - 998.5 ml/l of a hydrophobic liquid,

0.5 - 100 ml/l of an emulsifier, and

1 - 100 g/l of a crosslinking agent for a
 polysaccharide,

b) 50 - 95% by volume of a discontinuous phase containing:

950 - 997 ml/l of water, and

3 - 50 g/l of a polysaccharide.

Like the emulsion of US Pat. No. 4,663,366 discussed above, the new emulsion makes use of an emulsion technique involving storing of reactants separately, one in each phase of the emulsion. When the reactants utilized in the new emulsion, viz. the polysaccharide and the crosslinking agent, come into contact with one another after the emulsion having been subjected to high shear forces, a crosslinking of the polysaccharide is taking place, resulting in a setting of the emulsion to a gelatinous solid substance.

The principle of the setting of the new plugging liquid is different from that of the plugging liquid of US Pat. No. 4,663,366. It is the crosslinking of the polysaccharide that causes the setting of the emulsion, whereas in the emulsion of US Pat. No. 4,663,366 a thickening takes place as a result of a swelling of the bentonite when the latter comes into contact with water. The setting achieved with the new plugging liquid of the invention is a substantially irreversible setting and has a good durability within the periods of time that are of interest in normal rig operations.

The mud system employed in well and formation treatment
operations consists of a number of units, each of which exerts
shear stress to a greater or lesser extent on the flowing
liquid. The shear stress is closely related to the pressure
drop in each individual unit. The highest pressure drop and
thus the highest shear stress occurs e.g. during the passage

of the nozzles in a drill bit or a port in a completion string down in a well. The use of the plugging liquid of the invention is based on the condition that only the nozzles of the drill bit or similar restrictions should produce a sufficiently high shear stress for the reactants (polysaccharide and crosslinking agent) to come into contact with one another, with a resulting crosslinking of the polysaccharide and setting of the liquid.

The hydrophobic liquid of the plugging liquid of the invention may advantageously be selected from mineral oils, vegetable oils, esters and ethers. It is selected on the basis of conventional criteriae such as viscosity, stability, compatibility with the drilling mud, environmental considerations and availability.

The polysaccharide serving to achieve the desired hardness of the emulsion may for instance be selected from any of the polysaccharides previously utilized for well control. The currently most preferred polysaccharides are xanthanes, alginates and scleroglucanes due to their combination of good crosslinking properties and viscosity characteristics.

Any of the commonly used crosslinking agents for polysaccharides may be used, especially such crosslinking agents that are stable at pH values in the range of 11 to 13. A preferred class of crosslinking agents is constituted by those containing divalent or trivalent metal ions as the active moiety. Examples of such crosslinking agents are Ca(OH)<sub>2</sub>, CaSO<sub>4</sub> and Al<sub>2</sub>(SO<sub>4</sub>)<sub>3</sub>. Another class of preferred crosslinking agents is constituted by aldehydes, such as glutaric aldehyde.

In addition to the above-mentioned main constituents the plugging liquid of the invention may contain a water-absorbing material in the continuous phase, i.e. the "oil" phase. As a water-absorbing material, a clay mineral would be preferred, in particular bentonite. By being incorporated in the "oil" phase, the water-absorbent material will be kept separated from the water contained in the aqueous phase, until the

20

25

30

emulsion is broken by being subjected to high shear forces. The water-absorbent material will then come into contact with the water contained in the aqueous phase of the emulsion and will absorb excess amounts thereof, whereby said water-absorbent material will undergo swelling, as explained above in the discussion of the plugging liquid of US Pat. No. 4,663,366. In the new plugging liquid, however, the primary function of the water-absorbent material is to absorb free water after the breaking of the emulsion and thus to prevent a shrinking of the material in Condition 2.

Preferably the plugging liquid of the invention comprises:

a) 20 - 40% by volume of a continuous phase containing:

900 - 997 ml/l of a hydrophobic liquid,

1 - 50 ml/l of an emulsifier, and

2 - 50 g/l of a crosslinking agent for a polysaccharide,

b) 60 - 80% by volume of a discontinuous phase containing:

970 - 995 ml/l of water, and

5 - 30 g/l of a polysaccharide.

A particularly preferred plugging liquid of the invention consists of a water-in-oil emulsion constituted by:

a) about 25% by volume of an oil phase containing:
about 968 ml/l of a low-aromatic lamp oil,
about 12 ml/l of an emulsifier on a triglyceride
basis,

about 16 g/l of bentonite, and about 24 g/l of calcium hydroxide,

b) about 75% by volume of an aqueous phase containing: about 992 ml/l of water and about 8 g/l of xanthane.

According to a variant of the invention, a plugging liquid of
the above-described sort may contain a weighting material in
addition to the constituents already mentioned, whereby the
plugging liquid may be used for inhibiting or preventing
undesired blow-outs in or from a well. The purpose of using a
weighting material in the plugging liquid is to increase the

density thereof so as to put the plugging liquid in a better condition to resist the blow-out pressure in the well.

A serious problem that may arise during the drilling of wells or in the production of oil and gas from wells is blow-out. Surface blow-outs occur when the drill bit cuts into a high pressure zone of gas, oil or water which can blow out the drilling mud and in serious cases even the drill stem with drill bit and other equipment and cause serious damage.

10 Underground blow-out occurs when a fluid in one porous formation flows into the well bore and then out of the well bore into another porous formation.

A common method of trying to stop blow-outs involves loading up the well with a slurry of weighting material, e.g. barite, under pressure and under conditions such that the barite is able to settle uniformly at the bottom of the well to form a hard plug, and then following up with a cement slurry in order to make the plug stronger and more permanent.

20

Another method consists in utilizing a slurry of a dry, powdered bentonite in diesel oil. When this slurry is mixed with the right amount of water, the bentonite will hydrate, yielding a stiff paste. If formed at the right time and at the right place, the mass may provide an effective plugging of the well, see for example US Pat. No. 3,082,823.

US Pat. No. 2,890,169 discloses plugging of a well with a plugging liquid prepared by forming first a slurry of an organophilic bentonite and cement in an oil, and then mixing the obtained slurry with a surfactant and water, to obtain a water-in-oil emulsion wherein the organophilic bentonite and the cement are dispersed in the continuous oil phase. As this emulsion is pumped down the well bore, the oil expands and flocculates the bentonite, which, under the right conditions, forms a filter cake on the well bore surface in the area to be plugged. This is then supposed to cause a filtration action which breaks the emulsion, whereby the emulsified water is brought into contact with the cement and reacts with the

cement to form a solid coating on the filter cake, which completes the plugging.

When the above-described new plugging liquid is used, with any necessary minor adaptations, together with a weighting material, it has been found that a better plugging effect can be achieved than with the slurries and emulsions containing weighting material heretofore employed for plugging well bores.

10

20

Thus, the invention also provides a plugging liquid on an emulsion basis for well control, containing a weighting material, which plugging liquid is characterized by being constituted by an emulsion comprising:

a) 5 - 50% by volume of a continuous phase containing:

800 - 998.5 ml/l of a hydrophobic liquid,

0.5 - 100 ml/l of an emulsifier, and

1 - 100 g/l of a crosslinking agent for a
polysaccharide,

b) 50 - 95% by volume of a discontinuous phase containing:

600 - 983 ml/l of water,

3 - 50 g/l of a polysaccharide, and

100 - 2500 g/l of a weighting material.

This variant of the new plugging liquid will be particularly useful in connection with underground blow-outs in those cases where it will be possible to pump the plugging liquid down the drill stem and through the drill bit. When the emulsion passes through the drill bit and consequently is subjected to high shear forces, a crosslinking of the polysaccharide is initiated by means of the crosslinking agent and the setting of the emulsion will make a substantial contribution to the well-killing effect achieved as a result of the high density of the emulsion.

15

Any weighting material can be used in the weighted plugging liquid of the invention. Exemplary weighting materials are barite, ilmenite, hematite, steel balls and calcium carbonate. A particularly suitable weighting material is barite.

30

35

The other constituents of the weighted plugging liquid of the invention, i.e. the hydrophobic liquid, the polysaccharide, the crosslinking agent for the polysaccharide, and the emulsifier, can be selected as for the non-weighted plugging liquid of the invention, as described above for said non-weighted plugging liquid.

When the plugging liquid of the invention is to be used for permanent closing of a well, the plugging liquid may also, if desired, contain an additive to prevent circulation loss, such as crushed nut shells or mica folium.

The weighted plugging liquid of the invention is preferably constituted by an emulsion comprising:

a) 5 - 50% by volume of a continuous phase containing:

800 - 998.5 ml/l of a hydrophobic liquid,

0.5 - 100 ml/l of an emulsifier, and

1 - 100 g/l of a crosslinking agent for a polysaccharide,

b) 50 - 95% by volume of a discontinuous phase containing:

600 - 983 ml/l of water,

3 - 50 g/l of a polysaccharide, and

100 - 2500 g/l of a weighting material.

More preferably, the weighted plugging liquid of the invention is constituted by an emulsion comprising:

a) 20 - 40% by volume of a continuous phase containing:

900 - 997 ml/l of a hydrophobic liquid,

1 - 50 ml/l of an emulsifier, and

2 - 50 g/l of a crosslinking agent for a
polysaccharide,

b) 60 - 80% by volume of a discontinuous phase containing:

620 - 850 ml/l of water,

5 - 30 g/l of a polysaccharide, and

100 - 2500 g/l of a weighting material.

A particularly preferred weighted plugging liquid of the invention is constituted by a water-in-oil emulsion consisting of:

a) about 25% by volume of an oil phase containing: about 968 ml/l of a low-aromatic lamp oil, about 12 ml/l of an emulsifier on a triglyceride basis,

about 16 g/l of bentonite, and about 24 g/l of calcium hydroxide,

b) about 75% by volume of an aqueous phase containing: about 682 ml/l of water, about 8 g/l of xanthane, and about 1300 g/l of barite.

The invention also provides a method for preparing the new plugging liquid, which method is characterized by mixing the hydrophobic liquid, the emulsifier, the crosslinking agent and any optional water-absorbent material to a mixture (a), mixing the water and the polysaccharide to a mixture (b), and introducing mixture (b) gradually into mixture (a) under agitation to form an emulsion of water in the hydrophofic liquid. When the plugging liquid shall contain a weighting material, said weighting material is incorporated into mixture (b) together with the water and the polysaccharide.

For the purpose of obtaining a stable emulsion it is common practice to include a suitable emulsifier in the continuous 25 phase. The emulsifier can be selected from a broad range of The emulsifier should commercially available emulsifiers. preferably have an alkali resistance such that it is stable in the pH range of 11 to 13 at typical drill hole temperatures. Emulsifiers on a triglyceride basis are very suitable for use  $_{
m 30}$  in the plugging liquid of the invention. Based on conventional criteriae which will be well known to those skilled in the art, such combinations of hydrophobic liquid and emulsifier are selected which will provide pH stability and the desired emulsion strength for handling and storing the emulsion, but 35 which result in a breaking of the emulsion when the emulsion is pumped through the nozzles of a drill bit down in a drill hole.

The invention further provides a method for plugging a zone of

15

a subterranean formation penetrated by a drill hole in fluid communication with said zone, in which method an aqueous plugging liquid containing a polysaccharide is injected into the zone via the drill hole, and is subjected to high shear forces in the drill hole, e.g. by passing through the nozzles of a drill bit. The method is characterized by there being used as plugging liquid an emulsion comprising:

a) 5 - 50% by volume of a continuous phase containing:

800 - 998.5 ml/l of a hydrophobic liquid,

0.5 - 100 ml/l of an emulsifier, and

1 - 100 g/l of a crosslinking agent for a
polysaccharide,

b) 50 - 95% by volume of a discontinuous phase containing:

950 - 997 ml/l of water, and

3 - 50 g/l of a polysaccharide,

whereby, as a result of the emulsion being subjected to said high shear forces, the polysaccharide and the crosslinking agent are brought into contact with one another, with a resulting initiation of crosslinking of the polysaccharide and setting of the plugging liquid.

The weighted variant of the plugging liquid of the invention is used primarily to inhibit or prevent undesired blow-outs in or from a well bore.

25

In Condition 1 the plugging liquid should be maintained under gentle agitation and at ambient temperature below 40°C. In preferred embodiments the plugging liquid contains no environmentally harmful or noxious constituents.

30

The plugging liquid of the invention is not affected by being pumped with a centrifugal pump or mud pump for several hours. However, when the emulsion is subjected to high shear forces, such as when it is forced through the nozzles of a drill bit at a pressure drop of 50 to 120 bars, e.g. about 100 bars, the emulsion sets markedly. The setting time for a non-weighted plugging liquid of the invention can be adjusted e.g. in the range of from 2 to 10 minutes, whereas the setting time for a weighted plugging liquid of the invention can be more appro-

priately adjusted to be within the range of from 2 seconds to 2 minutes, e.g. from 5 to 20 seconds.

The setting time can be predetermined through an appropriate selection of the amounts of crosslinking agent and emulsifier, especially the amount of emulsifier. An increased amount of emulsifier increases the setting time, whereas an increased amount of crosslinking agent reduces the setting time.

10 The preparation of the new plugging liquid and its characteristics are shown in more detail in the following examples.

## Example 1, Non-weighted plugging liquid.

One liter of a water-in-oil emulsion was prepared in the following manner. 0.75 l of water and 4.0 g of xanthane were mixed under agitation in a 2 l cup (Cup 1), and likewise 0.25 l "Exxsol D60", 3 ml "Emulsogen" (non-ionic fatty acid ester) and 5.0 g Ca(OH)<sub>2</sub> were mixed in another 2 l cup (Cup 2) under agitation. The mixture in Cup 1 was then added to the mixture in Cup 2 under agitation.

The obtained emulsion was pumped at a pressure of 60 bars through a nozzle and down into a cup where it set in the course of 5 minutes. After 24 hours the shearing stress was measured to be 6000 Pa.

During the setting of the emulsion, a certain amount of free water separated. This may be avoided by incorporating a water-absorbent material, such as bentonite, in the oil based mixture (Cup 2). This was made in Example 2.

#### Example 2. Non-weighted plugging liquid.

150 l of a water-in-oil emulsion were prepared, consisting of:

a) 25% by volume of an oil phase containing:

968 ml/l oil of "Exxsol D60",

12 ml/l of "Emulsogen",

16 g/l of bentonite,

24 g/l of calcium hydroxide,

b) about 75% by volume of an aqueous phase containing:

992 ml/l of water and 8 g/l of xanthane.

112 l of water and 900 g of xanthane in powdery form were

5 mixed in a 2200 l vessel (Vessel 1) equipped with a propeller mixer operated at 400 r.p.m.. 37 l of "Exxsol D60" (a low-aromatic lamp oil), 300 ml "Emulsogen" (non-ionic fatty acid ester), 900 g of milled Ca(OH)<sub>2</sub> and 600 g of bentonite i powder form were mixed in a 1200 l vessel (Vessel 2) equipped with a propeller mixer operated at 400 r.p.m. The xanthane mixture in Vessel 1 was then gradually transferred at about 20°C to Vessel 2 in 8 minutes under agitation at 400 r.p.m.

The obtained emulsion had a density of about 0.95 g/ml. It was not affected by being pumped with a centrifugal pump for 2 hours, during which period the temperature increased from 20 to 40°C. The test was repeated after 24 hours with the same result.

- Circular pumping with a centrifugal pump, leading to an increase of the temperature to 62°C, resulted in the emulsion setting in the mixing vessel in Condition 1. However, the shear stress was not measurable, and thus was lower than 200 Pa. This suggests that the stability is reduced when the temperature of the emulsion increases from 40°C to 60°C in the emulsion. However, since the set emulsion still remained in Condition 1, it could again be agitated to form a liquid, homogenous state.
- After having been subjected to a pressure drop of 100 bars through a needle valve the emulsion set markedly after 2 minutes. The following shearing stress values were measured at room temperature:

After 10 minutes:

8000 Pa

35 After 24 hours:

10-12.000 Pa

After 2 days (48 hours): 10-12.000 Pa.

No free water or oil was observed.

## Example 3. Weighted plugging liquid.

1.362 liters of a water-in-oil emulsion were prepared in the following manner. 0.75 l of water and 6.0 g of xanthane were mixed under agitation in a 2 l cup (Cup 1). The mixture was allowed to rest for 1 hour, whereupon 1800 g of ilmenite were added to the mixture. In another 2 l cup (Cup 2) 0.25 liter of "Exxsol D60", 1.0 ml "Safemul PE" (an emulsifier on a triglyceride basis) and 8.0 g of Ca(OH)<sub>2</sub> were mixed under agitation. The mixture in Cup 1 was then added to the mixture in Cup 2 under agitation. An emulsion having a density of 2.0 g/cm<sup>3</sup> was obtained.

The obtained emulsion was pumped at a pressure of 60 bars through a nozzle and into a cup where it set in the course of 15 1 minute. After 24 hours the shearing stress was measured to be 16000 Pa.

During the setting of the emulsion, a certain amount of free water separated. This may be avoided by incorporating a water20 absorbent material, such as bentonite, in the oil based mixture (Cup 2).

#### Example 4. Weighted plugging liquid.

- 1.375 liters of a water-in-oil emulsion were prepared in the following manner. 0.75 l of water and 6.0 g of xanthane were mixed under agitation in a 2 l cup (Cup 1). The mixture was allowed to stand for l hour, whereupon 1500 g of barite were added to the mixture. In another 2 l cup (Cup 2) 0.25 liter of "Exxsol D60", 1.0 ml "Safemul PE" (an emulsifier on a trigly-ceride basis) and 8.0 g of Ca(OH)<sub>2</sub> were mixed under agitation. The mixture in Cup 1 was then added to the mixture in Cup 2 under agitation. An emulsion having a density of 1.80 g/cm<sup>3</sup> was obtained.
- The obtained emulsion was pumped at a pressure of 60 bars through a nozzle and into a cup where it set in the course of 2 minutes. After 24 hours the shearing stress was measured to be 14000 Pa.

During the setting of the emulsion, a certain amount of free water separated out. This may be avoided by incorporating a water-absorbent material, such as bentonite, in the oil based mixture (Cup 2).

15

#### Patent claims

A plugging liquid for plugging a zone of a subterranean
 formation around a drill hole, consisting of an aqueous liquid containing a polysaccharide,

c h a r a c t e r i z e d in that it is constituted by an emulsion comprising:

a) 5 - 50% by volume of a continuous phase containing:

800 - 998.5 ml/l of a hydrophobic liquid,

0.5 - 100 ml/l of an emulsifier, and

1 - 100 g/l of a crosslinking agent for a
 polysaccharide,

b) 50 - 95% by volume of a discontinuous phase containing:

950 - 997 ml/l of water, and

3 - 50 g/l of a polysaccharide.

2. The plugging liquid according to claim 1,

characterized in that it comprises:

a) 20 - 40% by volume of a continuous phase containing:

900 - 997 ml/l of a hydrophobic liquid,

1 - 50 ml/l of an emulsifier, and

2 - 50 g/l of a crosslinking agent for a polysaccharide,

b) 60 - 80% by volume of a discontinuous phase containing:

970 - 995 ml/l of water, and

5 - 30 g/l of a polysaccharide.

- The plugging liquid according to claim 1 or 2,
- och aracterized in that the hydrophobic liquid is selected from mineral oils, vegetable oils, esters and ethers.
- 4. The plugging liquid according to any of claims 1 to 3, c h a r a c t e r i z e d in that the crosslinking agent for crosslinking the polysaccharide contains divalent or trivalent metal ions as the active moiety.
  - 5. The plugging liquid according to any of claims 1 to 3, c h a r a c t e r i z e d in that the crosslinking agent is

an aldehyde.

- 6. The plugging liquid according to any of claims 1 to 5, c h a r a c t e r i z e d in that the polysaccharide is a santhane, an alginate or a scleroglucane.
  - 7. The plugging liquid according to any of claims 1 to 6, c h a r a c t e r i z e d in that the hydrophobic liquid contains a water-absorbing material.
  - 8. The plugging liquid according to claim 7, c h a r a c t e r i z e d in that the water-absorbing material is a clay mineral, especially bentonite.
- of the plugging liquid according to any of claims 1 to 8, character ized in that the emulsifier has an alkali resistance such that it is stable at pH 11 to 13.
- 10. The plugging liquid according to claim 9,
  20 c h a r a c t e r i z e d in that the emulsifier is on a triglyceride basis.
- 11. The plugging liquid according to any of claims 1 to 10, c h a r a c t e r i z e d in that it is a water-in-oil emulsion consisting of:
  - a) about 25% by volume of an oil phase containing:
    about 968 ml/l of a low-aromatic lamp oil,
    about 12 ml/l of an emulsifier on triglyceride
    basis,

about 16 g/l of bentonite, and about 24 g/l of calcium hydroxide,

- b) about 75% by volume of an aqueous phase containing: about 992 ml/l of water and about 8 g/l of xanthane.
- 12. A method for plugging a zone of a subterranean formation penetrated by a drill hole in fluid communication with said zon, in which an aqueous plugging liquid containing a polysaccharide is injected into said zone via the drill hole,

and is subjected to high shear forces in the drill hole, e.g. by passing through the nozzles of a drill bit, c h a r a c t e r i z e d by there being used as plugging

liquid an emulsion comprising:

a) 5 - 50% by volume of a continuous phase containing:

800 - 998.5 ml/l of a hydrophobic liquid,

0.5 - 100 ml/l of an emulsifier, and

1 - 100 g/l of a crosslinking agent for a
 polysaccharide,

b) 50 - 95% by volume of a discontinuous phase containing:

950 - 997. ml/l of water, and

3 - 50 g/l of a polysaccharide,

whereby, as a result of the emulsion being subjected to said high shear forces, the polysaccharide and the crosslinking agent are brought into contact with one another, with a resulting initiation of crosslinking of the polysaccharide and setting of the plugging liquid.

- 13. The method according to claim 12,
- characterized by there being used a plugging liquid according to any of claims 2 to 11.
  - 14. A plugging liquid on an emulsion basis for well control, containing a weighting material,
- 25 characterized in that it is constituted by an emusion comprising:
  - a) 5 50% by volume of a continuous phase containing:

800 - 998.5 ml/l of a hydrophobic liquid,

0.5 - 100 ml/l of an emulsifier, and

b) 50 - 95% by volume of a discontinuous phase containing:

600 - 983 ml/l of water,

3 - 50 g/l of a polysaccharide, and

100 - 2500 q/l of a weighting material.

- 15. The plugging liquid according to claim 14,
- characterized in that it comprises:
  - a) 20 40% by volume of a continuous phase containing:

30

900 - 997 ml/l of a hydrophobic liquid,
1 - 50 ml/l of an emulsifier, and
2 - 50 g/l of a crosslinking agent for a polysaccharide,

b) 60 - 80% by volume of a discontinuous phase containing:

650 - 850 ml/l of water, 5 - 30 g/l of a polysaccharide, and 1000 - 2500 g/l of a weighting material.

- 10 16. The plugging liquid according to claim 14 or 15, c h a r a c t e r i z e d in that the hydrophobic liquid is selected from mineral oils, vegetable oils, esters and ethers.
- 17. The plugging liquid according to any of claims 14 to 16, characterized in that the crosslinking agent for crosslinking the polysaccharide contains divalent or trivalent metal ions as the active moiety.
- 18. The plugging liquid according to any of claims 14 to 17, characterized in that the crosslinking agent is an aldehyde.
- 19. The plugging liquid according to any of claims 14 to 18, c h a r a c t e r i z e d in that the polysaccharide is a zanthane, an alginate or a scleroglucane.
  - 20. The plugging liquid according to any of claims 14 to 19, c h a r a c t e r i z e d in that the emulsifier is on a triglyceride basis.
  - 21. The plugging liquid according to any of claims 14 to 20, c h a r a c t e r i z e d in that hydrophobic liquid contains a water-absorbing material.
- 25 22. The plugging liquid according to claim 21, c h a r a c t e r i z e d in that the water-absorbing material is a clay mineral, especially bentonite.
  - 23. The plugging liquid according to any of claims 14 to 22,

20

characterized in that the weighting material is selected from barite, ilmenite, hematite, steel balls and potassium carbonate.

- 5 24. The plugging liquid according to claim 23, characterized in that the weighting material is barite.
- 25. The plugging liquid according to any of claims 19 to 24, 10 c h a r a c t e r i z e d in that it is a water-in-oil emulsion consisting of:
  - a) about 25% by volume of an oil phase containing: about 968 ml/l of a low-aromatic lamp oil, about 12 ml/l of an emulsifier on a triglyceride basis,

about 16 g/l of bentonite, and about 24 g/l of calcium hydroxide,

- b) about 75% by volume of an aqueous phase containing:

  about 682 ml/l of water,

  about 8 g/l of xanthane, and

  about 1300 g/l of barite.
- 26. The plugging liquid according to any of claims 14 to 25, c h a r a c t e r i z e d in that the emulsifier has an alkali resistance such that it is stable at pH 11 to 13.
  - 27. A method for preparing a plugging liquid according to any of claims 14 to 26,
- characterized by mixing the hydrophobic liquid,
  the emulsifier, the crosslinking agent and optional waterabsorbent material to form a mixture (a), mixing the water,
  the polysaccharide and the weighting material to form a
  mixture (b), and introducing mixture (b) gradually into
  mixture (a) under agitation to form an emulsion of water in
  the hydrophobic liquid.
  - 28. A use of a plugging liquid according to any of claims 14 to 26 for inhibiting or preventing an undesired blow-out in or from a well.

## INTERNATIONAL SEARCH REPORT

International application No. PCT/NO 94/00097

	FC17110 347 0	
A. CLASSIFICATION OF SUBJECT MATTER		
IPC: C09K 7/02, C09K 7/06 According to International Patent Classification (IPC) or to both r	·	
	ational classification and IPC	
FIELDS SEARCHED  Minimum documentation searched (classification system followed to	oy classification symbols)	
Withingth documentation sea circle (seaming or seasons)		•
IPC : CO9K		
Documentation searched other than minimum documentation to the	ne extent that such documents are included	in the fields searched
SE,DK,FI,NO classes as above		
Electronic data base consulted during the international search (nam	e of data base and, where practicable, searc	ch terms used)
EDOC, WPI, USPM, CLAIMS, JAPIO		
C. DOCUMENTS CONSIDERED TO BE RELEVANT		·
Category* Citation of document, with indication, where a	ppropriate, of the relevant passages	Relevant to claim No.
US, A, 3979303 (K S KANG ET AL. (07.09.76), claims 1,3,4,8	), 7 Sept 1976	1,12,14,27,
A EP, A2, 0226250 (SHELL INTERNAT MAATSCHAPPIJ B.V.), 24 June page 2, line 47 - line 49,	1987 (24.06.87),	1,12,14,27,
A EP, A2, 0137538 (SHELL INTERNAT MAATSCHAPPIJ), 17 April 198 line 1 - page 2, line 29	IONALE RESEARCH 5 (17.04.85), page 1,	1,12,14,27, 28
A EP, A1, 0128661 (ALLIED COLLOID 19 December 1984 (19.12.84)	S LIMITED), , claims 1,18,19	1,12,14,27,
The state of the s	See notest family and	AY
Further documents are listed in the continuation of B  Special categories of cited documents  A document defining the general state of the art which is not considere to be of particular relevance	T later document published after the i	nternational filing date or priority plication but cited to understand
"E" ertier document but published on or after the international filing date.  "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other.	considered novel or cannot be considered novel or cannot be considered the document is taken alo	idered to involve an inventive one
special reason (as specified)  Of document referring to an oral disclosure, use, exhibition or other means	"Y" document of particular relevance: the considered to involve an inventive a combined with one or more obtained being obvious to a person skilled in	tep when the document is uch documents, such combination
"P" document published prior to the international filing date but later the the priority date claimed	"&" document member of the same pate	
Date of the actual completion of the international search	Date of mailing of the internationa	l search report
17 August 1994	0 2 -09- 1994	
Name and mailing address of the ISA/	Authorized officer	
Swedish Patent Office Box 5055, S-102 42 STOCKHOLM	INGA-KARIN PETERSSON Telephone No. +46 8 782 25 00	1
Facsimile No. + 46 8 666 02 86	1 1 diopitorio 140 40 0 102 25 00	

## INTERNATIONAL SEARCH REPORT

International application No.
PCT/NO 94/00097

	<b>]</b> '	C17110 347 0	
C (Continue	ation). DOCUMENTS CONSIDERED TO BE RELEVANT		
	Citation of document, with indication, where appropriate, of the releva	nt passages	Relevant to claim No.
A	Derwent's abstract, No 89-307380/42, week 8942, ABSTRACT OF SU, 1447832 (UKHTINSK), 30 December 1988 (30.12.88)	<del></del>	1,12,14,27, 28
ŀ			
{			
ì			
j			·
ţ	,		
ſ			
}			İ
ļ			
j			
į			
-			
ĺ			
ł			
į			
]			
ĺ			
{			
l			
į			
1			<b>{</b>
}			
ì			
-			
ľ			
1			
j			
1			
ļ			1
1			
1			1
j			{
J			
•			
1			
ľ			
ł			
ļ			
j			
İ			
1			
ŀ			(.
1			1
. 1			}
	A/210 (continuation of second sheet) (July 1992)		<del></del>

#### INTERNATIONAL SEARCH REPORT

International application No. PCT/NO 94/00097

Observations where certain claims were found unsearchable (Continuation of Item 1 of first sheet) Box I This international search report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons: Claims Nos.: because they relate to subject matter not required to be searched by this Authority, namely: Claims Nos.: because they relate to parts of the international application that do not comply with the prescribed requirements to such an extent that no meaningful international search can be carried out, specifically: Claims Nos.: 4-7,9,11,17-21,23,25-26 because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a). Observations where unity of invention is lacking (Continuation of item 2 of first sheet) Box II This International Searching Authority found multiple inventions in this international application, as follows: As all required additional search fees were timely paid by the applicant, this international search report covers all searchable claims. As all searchable claims could be searched without effort justifying an additional fee, this Authority did not invite payment of any additional fee. As only some of the required additional search fees were timely paid by the applicant, this international search report covers only those claims for which fees were paid, specifically claims Nos .: No required additional search fees were timely paid by the applicant. Consequently, this international search report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.: The additional search fees were accompanied by the applicant's protest. Remark on Protest No protest accompanied the payment of additional search fees.

Form PCT/ISA/210 (continuation of first sheet (1)) (July 1992)



International application No. PCT/NO 94/00097

Information on patent family members

02/07/94

Patent document cited in search report		Publication date	Patent family member(s)		Publication date	
JS-A-	3979303	07/09/76	NONE			
P-A2-	0226250	24/06/87	DE-A-	3681133	02/10/91	
, , , ,	<b>V</b>	,	JP-A-	62153328	08/07/87	
			US-A-	4803264	07/02/89	
P-A2-	0137538	17/04/85	SE-T3-	0137538		
., 112	020/000	<b>20, 00, 1</b>	AU-A-	2971489	24/08/89	
			AU-A-	3276184	14/03/85	
			CA-A-	1232820	16/02/88	
			JP-B-	6015634	02/03/94	
			JP-A-	60072938	25/04/85	
			US-A-	4670167	02/06/87	
			CA-A-	1231616	19/01/88	
			US-A-	4670550.	02/06/87	
P-A1-	0128661	19/12/84	AU-B-	581616	02/03/89	
	V-2-0-0-	,,	AU-A-	2806784	22/11/84	
			CA-A-	1239014	12/07/88	
			JP-A-	59233092	27/12/84	
		•	US-A-	4571422	18/02/86	
			US-A-	4950747	21/08/90	
			US-A-	4950748	21/08/90	

Form PCT/ISA/210 (patent family annex) (July 1992)